علوم و فناوری جوشکاری ایران، سال سوم، شماره 1، بهار و تابستان 1396، صفحه 20-10

ارزیابی خواص اتصال غیرهمجنس فولاد زنگ‌نزن آستنیتی A321 به فولاد کربنی A537CL1 به روش GTAW

بهنام صادقی[1] ، حسن شریفی[1و2*] ، مهدی رفیعی[1]

1- مرکز تحقیقات مواد پیشرفته، دانشکده مهندسی مواد، واحد نجف آباد، دانشگاه آزاد اسلامی، نجف آباد، ایران.

2- گروه مهندسی مواد، دانشکده فنی و مهندسی، دانشگاه شهرکرد، شهرکرد، ایران

(دریافت مقاله: 1395/01/22 ؛ دریافت نسخهٔ نهایی: 1395/08/19)

چکیده

در این پژوهش ریزساختار و رفتار مکانیکی اتصال غیرهمجنس فولاد زنگ‌نزن آستنیتی AISI 321 به فولاد کربنی ASTM A537CL1 بررسی شد. بدین منظور از روش جوشکاری قوسی تنگستن-گاز و فلز پرکننده ER 308L با قطر 1/8 میلیمتر استفاده شد. جهت بررسی ریزساختار و مقطع شکست نمونه‌های جوشکاری‌شده از میکروسکوپ نوری و میکروسکوپ الکترونی روبشی استفاده شد. همچنین به‌منظور بررسی خواص مکانیکی اتصال، از آزمون‌های ضربه، کشش و ریزسختی‌سنجی در راستای عمود بر فلز جوش استفاده شد. نتایج نشان داد که ریزساختار فلز جوش به‌صورت آستنیتی به همراه فریت اسکلتی است که در برخی از قسمت‌های فلز جوش فریت شبکه‌ای نیز مشاهده شد. در آزمون کشش تمامی نمونه‌ها از فلز پایه فولاد کربنی ASTM A537CL1 و به‌صورت نرم دچار شکست شدند. فلز جوش مقدار انرژی ضربه بالایی در حدود 205 ژول از خود نشان داد.

کلمات کلیدی: اتصال غیرهمجنس، جوشکاریGTAW ، فولاد زنگ‌نزن آستنیتی، فولاد کربنی، خواص مکانیکی، ریزساختار.

Evaluation of dissimilar joint properties of A321 austenitic stainless steel to A537CL1 carbon steel by GTAW process

B. Sadeghi[1], H. Sharifi[1,2*], M. Rafiei[1]

1-Advanced Materials Research Center, Department of Materials Engineering, Najafabad Branch, Islamic Azad University, Najafabad, Iran.

2-Department of Materials Engineering, Faculty of Engineering, Shahrekord University, Shahrekord. Iran.

(Received 10 April 2016 ; Accepted 9 November 2016)

* نویسنده مسئول، پست الکترونیکی: sharifi@eng.sku.ac.ir

[Downloaded from iutjournals.iut.ac.ir on 2026-11-29]

[Downloaded from iutjournals.iut.ac.ir on 2026-11

Abstract

In this research, the microstructure and mechanical behavior of dissimilar joint of AISI 321 stainless steel to ASTM A57CL1 were studied. For this purpose, the GTAW process and ER 308L filler metal with diameter of 1.8 mm were used. In order to study the microstructure and fracture surface of weld samples, optical microscope and scanning electron microscope (SEM) were used. Also, the mechanical behavior of the joint was examined by impact, tension and microhardness tests. It was found that the microstructure of weld metal was austenite with skeletal ferrite. Also in some areas the lacy ferrite was seen. All samples were fractured from ASTM A537CL1 steel with a ductile manner during the tension test. The weld metal indicated high impact energy about 205 J.

Keywords: Dissimilar Joint, GTAW Welding, Austenitic Stainless Steel, Carbon Steel, Mechanical Properties, Microstructure.